

D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 1 of 6

Glysantin® G64® is an engine coolant concentrate based on ethylene glycol that needs to be diluted with water before use.

Glysantin® G64® contains a corrosion inhibitor package based on salts of organic acids, phosphate and silicate (PSi-OAT coolant). Glysantin® G64® is free of nitrites, amines and borates.

Properties

Glysantin® G64® protects engines from corrosion, overheating and frost. It effectively protects engines against corrosion.

Glysantin® G64® protects engines with an elevated temperature profile from the formation of deposits from flux and corrosion in the cooling system with its vital ducts in engine block and cylinder head, the radiator, the heater core and the water pump.

Glysantin® G64® protects heavy duty diesel engines from pitting of the cylinder liners. It fulfills the ASTM D7583 requirements.

Glysantin ® G64® fulfills the requirements of the following coolant standards:

ASTM D3306, ASTM D4985, ASTM D6210, ASTM D7583, SAE J1034, ÖNORM V 5123, CUNA NC 956-16, PN-C40007:2000, AS 2108-2004, JIS K 2234:2006, SANS 1251:2005, GB 29743-2013 and BS 6580:2010.

Glysantin ® G64® is officially approved by

Volvo Cars

TR-31854114-002





D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 2 of 6

Miscibility

Since the special advantages of Glysantin® G64® will only be achieved when Glysantin® G64® is used exclusively. Mixing of Glysantin® G64® with other engine coolants is not recommended.

Glysantin® G64® should be blended with water in a concentration of 33 to 60% by volume prior to use. The usage of a 50/50 ratio for the mixture of water and Glysantin® G64® is generally recommended.

For preparation of the coolant it is recommended to use distilled or deionized water. In most cases tap water is also appropriate.

Analysis values of the water may not exceed the following threshold values:

Water hardness: 0 - 3.6 mmol/lChloride content: $\max 100 \text{ ppm}$ Sulfate content: $\max 100 \text{ ppm}$

Chemical nature

Ethylene glycol with corrosion inhibitors

Appearance

Clear liquid without solid contaminants

Physical data

Density at 20 °C	1.124 – 1.128 g/cm³	DIN 51 757-4
Refractive Index, 20°C	1,431 – 1,434	DIN 51 423-2
Boiling point	min 160 °C	ASTM D 112
Flash point	min 120 °C	DIN ISO 2592
pH value	8.4 - 8.9	ASTM D 1287
pH value, 50 vol%	7.5 – 8.5	ASTM D 1287
Reserve alkalinity	8.0 – 10.0 ml	ASTM D 1121
Water content	max 5.0 %	DIN 51 777-1






D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 3 of 6

Frost protection Freezing point ASTM D 1177

50 vol% solution below -37 °C 33 vol% solution below -18 °C

Frost Protection of Glysantin® G64®



Corrosion Test data

Glassware Corrosion Test

ASTM D 1384

Metal coupons	Typical weight change mg / coupon	ASTM D 3306 limit mg / coupon
Copper	0	10 max
Solder	0	30 max
Brass	-1	10 max
Steel	0	10 max
Cast Iron	1	10 max
Cast aluminum	1	30 max





D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 4 of 6

Simulated Service Corrosion Test	ASTM D 2570			
	Metal coupons	Typical weight change mg / coupon	ASTM D 3306 limit mg / coupon	
	Copper Solder Brass Steel Cast Iron Cast aluminum	-1 -11 -2 -1 0 1	20 max 60 max 20 max 20 max 20 max 60 max	
Cavitation Erosion Corrosion Test	ASTM D 2809 Pump rating	10	min. 8	
Heat Transfer Corrosion Test	ASTM D 4340			
	Weight loss:	- 0.06 mg / cm ² / week	1.0 max	
Coolant Cavitation Test	ASTM D 7583	103 200 max		
	Pit counts			
Stability	Inhibitor-Stability after 168 h	clear, no- precipitation		
	Hard water stability after 10 days	clear, no- precipitation	VW PV 1426	
Foaming characteristics	33 vol % solution	max 50 ml / 3 s	ASTM D 1881	
i Janning Characteristics	55 voi /0 30idiloli	111dx 30 1111 / 3 3	7.0 TW D 1001	





D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 5 of 6

Quality Control

The above-listed data represent average values at the time of going to press of this Data Sheet. They are intended as a guide to facilitate handling and cannot be regarded as specified data. Specified product data are issued as a separate product specification.

Storage Stability

Glysantin® G64® has a shelf life of at least three years when stored in originally closed, air-tight containers at temperatures of maximum 30 °C. Do not use galvanized containers for storage.

Color

Glysantin® G64® is usually available in green.





D/EVO 137 e September 2016 Supersedes edition of August 2016

Page 6 of 6

Safety

When using this product, the information and advice given in our Safety Data Sheet should be observed. Due attention should also be given to the precautions necessary for handling chemicals

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

September 2016

www.glysantin.de

BASF SE
Fuel and Lubricant Solutions
67056 Ludwigshafen, Deutschland
©=registered trademark of BASF SE

